


Polyimide (PI)



Description



Polyimide (PI) materials are characterized by a ring-shaped molecular structure containing nitrogen and because of its high-performance polyimide offers a broad combination of temperature resistance, chemical resistance, mechanical toughness, natural lubricity, wear-resistance & insulation properties. PI is one of the highest performing engineering plastics currently available. Polyimide (PI) will not melt and can operate continuously from cryogenic temperatures to 550°F (288°C), with excursions to 900°F (482°C). Polyimide (PI) consistently exhibit superior performance in a variety of applications requiring low wear and long life in hostile environments.

Typical properties

Mechanical Property	Temperature	ASTM	Units	Typical Values
Tensile Strength	23 °C	D-1708	MPa (kpsi)	90
	260 °C			42
Strain at Break	23 °C	D-1708	%	8
	260 °C			7.5
Flexural Strength	23 °C	D-790	MPa (kpsi)	110
	260 °C			60
Flexural Modulus	23 °C	D-790	MPa (kpsi)	3100
	260 °C			1700
Shear Strength	23 °C	D-732	MPa (kpsi)	90
Izod Unnotched Impact Strength	23 °C	D-256	J /m	120
Poisson's Ratio	23 °C	—	—	0.4
Surface resistivity	23 °C	D257	Ω·m	—
Coefficient of thermal expansion	23 °C	D696	μm/m/°C	50
Friction coefficient	—	—	—	0.29
Water Absorption	23 °C (24h)	D570	%	—
Density	g/Cm3	D792		1.34

Application

Aerospace: Bushings, seals, thrust washers, vacuum-environment structural parts;
Automotive & E-mobility: E-axle bearing insulation, transmission seal rings, turbocharger components, shift-fork pads, hydrogen-valve seats & packings;
Semiconductor: Low-outgassing vacuum components, insulators;
Energy & Fluid handling: Compressor rider bands, pump piston rings, high-temperature sealing elements;
Industrial equipment: High-temperature bearings, wear rings, non-abrasive sliding parts against aluminium alloy;



Contact information goes here:

Quilliant Tech Co.,Ltd.
 HQ:Room 2023, Building B
 Zhongjinguoji Square,No.333, North
 Caoxi Road,Shanghai China.

Quilliant Advanced Material Pte Ltd.
 Registration office: 133 New Bridge
 Road #10-03 China Town point
 Singapore 059413

Email: info@quilliant-tech.com
www.quilliant-tech.com

Notice: This TDS is provided for informational purposes only. To the best of our knowledge, the information is accurate, but it is offered without any representation or warranty, either express or implied. The property values stated are based on tests of laboratory specimens and individual customer experiences; these values may not be achieved in every end-product application due to variations in manufacturing processes. Nothing in this document shall be construed as granting a license under any patent or as permission or encouragement to practice any method that infringes any patent. Quilliant Tech. shall not be held liable for any claims, damages, or losses arising from the use of, or reliance on, this information or the application of our supplied products.